

# Sempre Igloo

## Renders and paints cure accelerator



### Characteristics

- allows rendering and painting at 0 ° C
- allows rendering and painting in high humidity (up to about 80%)
- speeds up the evaporation of water
- easy to use
- neutral for the rest of the material properties

### Scope of use

This allows rendering and painting at 0 ° C - recommended for Tesoro Acrylic Render and Eterna Acrylic Paint application at reduced temperatures (0 - 10 ° C) and high humidity (up to about 80%).

### Application

Sempre Igloo should be added to the render or paint before use. It is recommended that compliance with the proportions of the measure should not constitute more than 1% by weight of plaster or paint that is up to 250 ml (whole bottle) per 25 kg bucket of render and 150 ml (3/5 bottles) per 10 liter of paint. After thorough mixing, application can proceed to the surface. Painted or plastered surface can not be frozen. The recommended temperature for work is from 0°C to 10°C. Freshly applied paint or render achieves resistance to rain after about 4-6 hours, depending on the temperature and humidity.

### Other information

The product has been classified as dangerous according to the rules. Highly flammable. Irritating to eyes. Vapours may cause drowsiness and dizziness.

**Should you need support or advice, please consult our advisory service for architects and contractors on the hotline number:  
Phone: + 353 1 40 30 811  
e-mail: [info@sempretherm.ie](mailto:info@sempretherm.ie)**

Technical Data Sheet  
No. 3.SI  
05.07.2011



### Storage

Up to 12 months since the production date when stored in cold conditions and in original undamaged packages.  
**Protect against frost!**

### Packaging

0.25 ltr, 24 pcs / box

### Technical data

Bulk density:	0.88 gr / cm <sup>3</sup>
Temperature of application:	from +0 °C to +10 °C
Drying time:	approx. 4-6 h

Apart from the information given here it is also important to observe the relevant guidelines and regulations of various organisations and trade associations as well as the respective standards. The aforementioned characteristics are based on practical experience and applied testing. Warranted properties and possible uses which go beyond those warranted in this information sheet require our written confirmation. All data given was obtained at an ambient and material temperature of +23 °C and 50 % relative air humidity unless specified otherwise. Please note that under other climatic conditions hardening can be accelerated or delayed.

The information contained herein, particularly recommendations for the handling and use of our products, is based on our professional experience. As materials and conditions may vary with each intended application, and thus are beyond our sphere of influence, we strongly recommend that in each case sufficient tests are conducted to check the suitability of our products for their intended use. Legal liability cannot be accepted on the basis of the contents of this data sheet or any verbal advice given, unless there is a case of wilful misconduct or gross negligence on our part. This technical data sheet supersedes all previous editions relevant to this product.

**neotherm**  
approved distributor **sempre therm**

[www.neotherm.ie](http://www.neotherm.ie)

[www.sempretherm.ie](http://www.sempretherm.ie)

[info@neotherm.ie](mailto:info@neotherm.ie)

Manufacturer: Sempre Farby Sp. z o.o.  
ul. Gen. Kuźnia 60, Bielsko-Biala, Poland  
+48 33 496 06 09, [info@semprefarby.pl](mailto:info@semprefarby.pl)

Dublin: Unit 31 Crag Avenue,  
Clondalkin Industrial Est., Dublin 22  
Office: 01 40 30 811

Limerick: Unit 5 Garryglass Industrial Est.  
Ballysimon, Limerick  
Office: 061 319 721